


Date: 28 March 2019

Test: U.V Exposure test - Real Time (Queensland, Australia 28.° S, 153.4000° E)

Duration: **9 months**


BM-33



Exposed side

Master


BM-15



Exposed side

Master


Competitor 3.4kg/sqm



Exposed side

Master

Competitor 1.6kg/sqm



Exposed side

Master

Notes:

The Boss Mat BM-33 shows negligible signs of colour loss but BM-15 is starting to show signs of colour degradation. Structurally, both samples are in very good physical condition.

The competitors products are showing complete colour loss on both samples. Structurally, both samples are now very brittle.